

# FICHE TECHNIQUE



# COPY 3 OFFICE

Caractéristiques	Méthode de mesure	Unité	Moyenne	Min	Max
Taux d'humidité	ISO 287 E.d.P	%	4,5	4,2	4,8
Grammage	ISO 536 I.O 10 P44 004	g/m <sup>2</sup>	<b>80</b>	78	82
Epaisseur	ISO 534 I.O 10 P44 005	μ	<b>102</b>	96	108
Blancheur CIE	ISO 11475 I.O 10 P44 006		<b>147</b>	144	150
Opacité	ISO 2471 I.O 10 P44 006	%		91	
Rugosité (Bendtsen)	ISO 8791/2 I.O 10 P44 007	ml/1'	200	100	300



**EFP**

**8, rue des Graviers**

**92200 Neuilly-sur-Seine**

**Tél. : 01 46 40 11 00 - Fax : 01 46 40 10 60**

**Contacts :**

**Bruno CHATEL - Port. 06.79.70.22.93 - bc@efp-chavassieu.com**

**Véronique BAFFREAU - Tél. : 01.46.40.72.05 - vbaffreau@efp-chavassieu.com**